In recent years, from a viewpoint of environmental problem and improvement in safety at corrosion, weight saving of an automobile and rigidity enhancement of a member are progressed. Among them, as a structural member of an automobile, use of a hollow (weight-saving) cross-section closed (rigidity enhancing) steel pipe is increased. Recently, a demand for a steel pipe having a higher strength and excellent processibility is being increased.

A high strength high ductile HISTORY steel pipe having a microtissue is a steel pipe which was developed in response to this demand, and is manufactured by a new steel pipe process "HISTORY (high speed tube welding and optimum reducing technology)".

Characteristics of a high strength high ductile HISTORY steel pipe and its bending processibility will be introduced.

An outline of a manufacturing process is shown in Fig.1. A coil-like band steel is molded into a pipe by a low distortion molding method (CBR mill), both edges are heat-melted by induced current, and are connected with a squeeze roll. An electrically seamed welded steel pipe is subsequently subjected to warm highly diameter-reducing rolling with a stretch reducer, and high strength high ductile HISTORY steel pipes having various external diameter wall thicknesses are manufactured.


(1) Since a metal tissue undergoes a great rolling distortion (diameter-reducing rolling) in a warm region, the metal tissue exhibits a fine particle tissue in which ferrite finely-divided as shown in Photo 1 and, at the same time, a second layer is also finely dispersed as shown in Photo

1. For this reason, as shown in Fig.2, a remarkably high elongation (EI) is obtained even at a high strength as compared with an electrically seamed steel pipe.

【物件名】

甲第3号証

甲第3号証



KAWATETSU



# 川崎製鉄技報

KAWASAKI STEEL GIHO

Vol.32 No.1 2000

【添付書類】 **/ || || || || || || || /2**0

自動車用材料特集号



自動車用材料特集号

日 次

巻 頭 宮

佐藤 锖

		_	*		•	•			
				•		•			
自動車用鋼	せの問題:	- 40 de			٠.		•		
日料平用牌								•	
	安田東	古君 修 滑	)野 芳一	· · · · · · · · · · · · · · · · · · ·		····			
								•	
成形性に優	れた自動場	【内外板に】	芽いられる剤	细坡					•
··	7846 mm	Link Pares	. J. J			•	•		·····
	五极 辛天	, 10 K KE 1/2		**************	• • • • • • • • • • • • • • • • • • • •	• • • • • • • • • • • • • • • • • • • •	• • • • • • • • • • • • • • • • • • • •		7
自動車用高	強度導鋼板	反の衝突エン	ネルギー吸収	特性と形状を	核性				
	濟水 伝菌	比良 医耶	4646 4999						
			- MA - A-IU			•••••••		***************	
48-9-11 45-	ر ويوملا شورات		***						
知ノリー日	则平态料?	ノク用作り	機被覆鋼板の	超行性		•			
	尾形 浩行	分野 十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二	一 望月 一雄	• • • • • • • • • • • • • • • • • • • •	••••••			• • • • • • • • • • • • • • • • • • • •	
北米5年走	行車の度が	t状況 ·							
	均用 学	2019 世	,	** .					26
	, , , , , , , , , , , , ,					*************		•••••	26
						•			
日野早朝ガ	ス規制強化	とに避合する	る高性能ステ	ンレス側			•	•	
	當崎 淳	平澤 淳一郎	佐藤 進				***************		
高阶度快技	一つ 田 泉地	スムム作品	の高強度化	44					
		ハロ <u>エMin</u>	*/ HD 28/28 161	74 TT->	•			•	
	于政義	上/画 略	• • . • . • . • . • . • . • . • . •	*****************	• • • • • • • • • • • • • • • • • • • •	• • • • • • • • • • • • • • • • • • • •	••••••	• • - • - • • • • • • • • •	
自動車用の	モータ鉄化	材料とその	)評価方法						
	本田 厘人	万田 具卷	島田 一里				•••••••		
	. —					• • • • • • • • • • • • • • • • • • • •	••••••••		43
00m #W									
CBR 成形ミ						'			
	豊岡 高明	橫本 裕二	都司 牧男			• • • • • • • • • • • • • • • • • • • •	·		
		•							
高寸法精度	<b>绝材,始和</b>	の陶器	•						
IN S WATHER	PUNTAL TAPPAR					•			
	小川 魔生	天田」	川等上语列	下 武志	***********	· · · · · · · · · · · · · · · · · · ·	••••••	· • • • • · · · • • • · • • • • · • · •	54
						•			
薄鋼板向け	連続鋳造ス	ラブの高洲	净化技術						
							·····		
		1317 7700			•••••••••••••••••••••••••••••••••••••••	************	•••••••	• • • • • • • • • • • • • • • • • • • •	60
			•						
〈新製品・新			٠						
成形性に優っ	ኪሎ TS980	MPa 经产	经工商公会会	鋼板「CHLY	men !		• • •		
				iiivia   Ollidi					
	भारत अरावा	亚华 秘法	************	• • • • • • • • • • • • • • • • • • • •	••••••	••••••	••••••••	• • • • • • • • • • • • • • • • • • • •	65
<u></u>									
歪み時効硬(	化により液	い衝撃吸収	【エネルギー	を示す 440M	Pa 級良加	工性熱關圧	延縮板		. •
	金子 真次	郎、脊坂、金	朝 富永 四一					•	
							••••••••••••••••••	••••••	
Z.K.A. 1, 201 A 1				<b>41 45 55 55 5</b>					
些性と的 2.	火加土脆色	に使れた数	一般り成形用	熱間圧延鋼板	[ KFN5]				•
	登坂 章男	古君修	桑子 浩						^~
		•						***************	
+\± . ++m.	77 167 3. 44	***							
寸法・材質の	ソバーな得	物以鴨の素	阿比些爵权						
	严部 後一	石川孝	網海 弘資	• • • • • • • • • • • • • • • • • • • •		*****	•••••••		
									/2
			-						

	4			
		-12	١.	
•	×	•		
		٦		
		,	٠.	

プレス成形性に優れた固形潤滑処理熱間圧延鋼板「M コート」 個貝 和彦 鈴木 幸子 海野 茂	•••••	••••••	••••••	74
触媒担体用耐能化性ステンレス鋼「R20-5USR」 維野 貞夫 佐藤 進		•••••		 76
曲げ加工性に優れた高強度高延性 HISTORY 鋼管 小山 康衡 ・豊岡 高明				 79
際折防止処理鉄粉「KIP クリーンミックス」 小倉 邦明 上ノ園 聡 尾崎 由紀子			· ·	 
極低スパッタ化を可能にしたパルス MAG 溶接用ワイヤ 「KM-50S」 片岡 時彦 版口 修一 佐々 仁孝	· · · · · · · · · · · · · · · · · · ·	<u>.</u>		85
プレス成形可能な樹脂パネル『KP シート』 花谷 誠二 久保 秀徳 西村 治			. •	 

.

新製品·新技術

川崎製鉄技報32 (2000) 1,79-81

### 曲げ加工性に優れた高強度高延性 HISTORY 鋼管"

小山 康衛+2 豊岡 高明+3

# High Strength and High Elongation Tubular Products "HISTORY Steel Tube" with Good Bendability

Yasue Koyama Takaaki Toyooka

#### 1 はじめに

近年、環境問題や衝突時の安全性向上の観点より、自動車の軽量 化と部材の高剛性化が進められている。その中で、自動車の標準部 材としては、中空(軽量化)で閉断面(高剛性化)の興管の使用が 増加している。最近は、より高強度で加工性に優れる興管のニーズ が高まっている。

敬細組織を有する高速度高延性 HISTORY 興管はこのニーズに応えるべく開発した鋼管であり、新しい鋼管のプロセス「HISTORY (high speed tube welding and optimum reducing technology)」によって製造される。

高強度高延性 HISTORY 鋼管の特徴とその曲げ加工性について紹介する。

#### 2 高強度高延性 HISTORY 鋼管の製造方法と特徴

#### 2.1 製造方法

Fig. 1 に製造プロセスの概略を示す。コイル状の帯側を低ひずみ 成形法(CBR ミル)によりパイプ状に成形し、両エッジを高層波 誘導電池で加熱溶融し、スクイズロールにて接合する。電纜溶接さ れた鋼管は、接続のストレッチレデューサーにで温間高縮径圧延ざ れ、種々の外径肉厚の高強度高延性 HISTORY 鋼管が製資される。

#### 2.2 組織および機械的性質の特徴

(1) 温間域で大きな圧延ひずみ(縮径圧延)を受けるため、金属 組織は Photo 1 に示すようにフェライトが機綱化するととも に第2層も微細分散した細粒組織を呈する。このため Fig. 2 に示すように電話網管に比べ高致度であっても著しく高い体び




20.00

ERW steel tube

HISTORY steel tube

Photo 1 Comparison of microstructure between ERW steel tube and HISTORY steel tube



KKW steel tube HISTORY steel tube

Fig. 2 Comparison of elongation between ERW steel tube and HISTORY steel tube by tensile test (No. 12 specimen of JIS Z 2201)




Fig. 1 Manufacturing process of high strength and high elongation HISTORY steel tube

<sup>\*\*</sup> 平成12年1月12日原稿受付




Fig. 3 Comparison of hardness distribution around welded seam between ERW and HISTORY steel tube with tensile strength of 780 MPa




Photo 2 Appearance of 3 points bending test (Bending radius: 30 mm)

	Size (mm)	TS (MPa)	YS (MPa)	EJ (%)
HISTORY	φ15 × r1.8	530	575	32
ERW	φ15×11.8	480	509	18






ERW steel tube

Photo 3 Comparison of bent tubes between ERW and HISTORY steel tubes after 3 points bending tests

(EI) が得られる。

(2) 電線溶接後の温間高縮径圧延により、アズロールのままで電 越路接部と母材部の暖さは Fig. 3 に示すように同等であり、 従来の電路鋼管のような後熱処理は不要である。

#### 高強度高延性 HISTORY 鋼管の曲げ加工性



**ERW** steel tube

HISTORY steel tube

Photo 4 Appearance of bent tubes of ERW and HISTORY steel tube after draw bending without internal plug (bending conditions:  $R = 150 \text{ mm} \times 20^{\circ}$ 

Table 1 Results of 3 points bending test for HISTORY steel tubes with tensile strength of 780 MPa; Tube size: φ25.4 × 13.0 mm, Bending conditions: bending radius = 50.8 mm, bending angle = 180°

Tensil	Shape after			
YS (MPa)	TS (MPa)	E1 (%)	YR (%)	bending
815	B45	34	96	Good
783	819	36	96	Good




Fig. 4 Available size range of HISTORY steel tube

して3点曲げ加工と引き曲げ加工をした結果を Photo 3、4 および Table 1 に示す。

高強度高延性 HISTORY 鋼管は強度が高いにもかかわらず電路鋼 管に比較し、 組伏 (Photo 3) 平座屈 (Photo 4) が起こりにくく、ま た、780 MPa 級の高張力頻管でも小曲げ半径の 180°3 点曲げが可

81

置顧整が不要であり、作業性の向上にも寄与できる。

#### 4 製造寸法範囲

HISTORY 個管の製造設備は 2000 年秋稼動の予定であり、Fig. 4 に示す範囲の領管寸法を製造する計画である。

#### 5 おわりに

ここでは主に HISTORY 鋼管の曲げ加工性を中心に紹介した。 HISTORY 鋼管は塑性加工全般わたり優れた加工性を示す。また、 高線径圧延による高能甲高生態性遠管も HISTORY 鋼管の大きな特 徴である。

自動車用爾管は今後ますます高張力化し、あわせて加工性の向上

も求められると思われるが、HISTORY 調管はこのニーズに十分応 えられるコストパフォーマンスに優れた製品である。

#### 〈聞い合わせ先〉

東京 〒100-0011 東京都千代田区内幸町2丁目2番3号 (日比谷国際ビル)

鋼管営業部鋼管グループ TEL 03(3597)4161

研管セクター室 TEL 03(3597)3510

名古墨 〒460-0088 名古墨市中区栄2丁目3季1号

(名古慶広小路ビル)

自動車鎖板営業グループ TEL 052(204)5321 大阪 〒530-8353 大阪市北区芝田1丁目1番4号

(仮急ターミナルビル)

鋼管営業部大阪鋼管グループ TEL 06(6315)4576

# 台) 川崎製鉄株式会社

〒651-0075 神戸市中央区北本町億1 丁目 1 828 号 〒100-0011 東京都千代田区内寺町2丁目2孝3号(日比谷国際ビル) 〒280-0835 千 敦 市 中 央 区 川 崎 町 1 書 地 〒475-8511 単 田 市 川 崎 町 1 丁 目 1 書 地 〒260-0835 千 東 市 中 央 区 川 崎 町 1 書 地 〒662-0925 西 宮 市 朝 田 町 1 書 50 号 〒712-8511 倉 敷 市 水 島 川 崎 週 1 丁 日 〒7263-0005 千 東 市 郷 毛 区 長 昭 町 351 各 地 電路(案內台) (078) 232-6111 電路(案內台) (033 3597-3111 電路(案內台) (033 3597-3111 金६년은 付) (043) 262-2021 電路(保持課) (045) 262-2024 電路(代表) (0789) 26-5507 電路(案內台) (086) 447-2020 電路(代 接)(043) 」 造研・発析 ・鉄橋事業部 造部 (無限) 中部 官工場 平675-0155 兵庫県加古郡排島町新 単数(代 度)(0794) 25-6111 電話(代 数) (0794) 33-6111 電話(総務第) (028) 677-5300 電話(建都)ループ (06) 6315-4511 電話(代 教) (052) 204-5311 電話(代 教) (011) 251-2551 電話(代 教) (011) 251-2551 電話(代 教) (011) 251-2551 電話(代 教) (017) 77-7121 電話(代 教) (017) 77-7121 電話(代 教) (035) 241-9111 電話(代 教) (035) 243-801 電話(代 教) (043) 323-801 電話(代 教) (0764) 41-2056 電話(代 教) (0767) 222-5200 電話(代 教) (0787) 822-5200 電話(代 教) (0787) 822-5100 電話(代 教) (0887) 822-5100 電話(代 教) (0897) 822-5100 世中 野海北 ш ` 营

New York Office (Kawasaki Steel America Inc.) Park Avenne Phasa. 55 East S2nd Street, New York, NY 10068, U.S.A.
Tel. New York (2121418-9120 Fax. New York (2121308-9292
Houston Office (Kawasaki Steel America Inc.) 800 Travia Soits 6376, Houston, TX 77002, U.S.A.

Tel. Houston (Ti) 384-9031 Fax. Houston (Ti) 385 Fax. Soits Srip, Houston, T. Front, C.S.

Tel. London (Ti) 383-1133, 1165 Fax. London (Ti) 383-1144

Düsselderf Office Kinsterstrasse 49, 4021 Düsselderf, Germany Tel. Dusselderf (211) 389910

Fax. Dusselderf (211) 389910

Singapore Office 15, Raffles Quay, No.15-03, Hong Loong Bldg., Singapore 044583 Tei. Singapore 220-1174

Fax. Singapore 224-5867

Bengkok Office Zad Floor, Abdulrahm Place 990, Rama W Road, Bangkok 18500, Thailand Tel Bangkok 536-1836 ~1300
Pax. Bengkok 636-1891

Jakarin Office 18th Floor Summitmes II JL. Jandrel Sudirmen Kav. 61-62 Jakarin 12190. Indonesia

Fax. Jakarta 522-8409

Martia Office 11th Floor, Allied Bank Center, 6754 Ayale Avenue, Maketi City, Morto Manila, Philippines

Fax. Manile 818-7563

Boljing Office 2225 China World Trade Center, No.1 Jianguomenwai Avenue, Beljing, Paople's Repubic of China

Tel. Belling Son-Soll Fer. Belling S60-5251

Fax. Hong Kong 537-5339

Shanghai Office Room 2505, Super Onem Bidg., 2103Yan An(W)Road, Shanghai, People's Republic of China Tel. Shanghai 6278-1418 Pax. Shanghai 6278-1418

Tel. Shringhal 5278-4415 Fax. Shanghal 5278-4418
Pito de Janeiro Office (Kawasaki Stael-Comercio e Siderurgia Little.) Preia de Botafogo. 228 Setor Salas 503 & 508, Botafago, Rio de Janeiro-RJ, Bratil Tel.Rio de Jeneiro-RJ, Bratil Tel.Rio de Jene

Vitoria Office (Kawasaski Shael-Cornércio • Siderurgia Lida.) Rus Eugenio Nato, 48-11 ander, Salas 1105 a 1106 CEP. 21065
Prais de Cante, Vitoria : Tel. Vitoria (27) 25-278 Fgz. Vitoria (27) 213-1225

	类员基	攤井 撤也	_			
川崎製鉄技報	委員	市田 歓郎	小川 正勝	中野 善文	加藤 俊之	橋本 正治
編集委員会		小池 武	小原 隆史	武内 健怡	片岡 健二	
	特集号數率	清野 芳一	安田 額			

## 川崎製鉄技報 KAWASAKI STEEL GIHO

第32巻 第1号 (通卷121号)

平成12年3月発行 (年4回発行)[非完品]

和行人 事并徵也

川崎製鉄株式会社 & 将 解

〒100-0011 京京都千代田区内幸町2-2-3(日上谷田庫ビル)

TEL #P 03(3597)3111 PAX 03(3597)4860, 4868

Published by

Kawasaki Steel Corporation Hibiya Kokusni Building, 2-2-3 Uchisaiwaicho, Chiyodaku, Tokyo 100-0011, Japan

TEL. Tokyo 03(3597)3111

川鉄テクノリサーチ株式会社

技術情報センター

〒100-0011 東京都千代田区内参町2-2-3(日上谷田田ビル) TEL M. 03(3597)4341 PAX 03(3597)4976

Technical Information Center

Kawasaki Steel Techno-research Corp.

Hiblya Kokusai Building, 2-2-3 Uchiasiwaicho, Chiyodaku, Tokyo 100-0011, Japan

田屋祭 大日本印刷株式会社

©Kawasaki Steel Corporation 1999

# This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

### **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:
☐ BLACK BORDERS
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
☐ FADED TEXT OR DRAWING
☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
☐ SKEWED/SLANTED IMAGES
☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
GRAY SCALE DOCUMENTS
☐ LINES OR MARKS ON ORIGINAL DOCUMENT
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

## IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.